

LISTING OF CLAIMS

1. (Currently amended) A print medium comprising:
an ink-receiving layer and a coated, absorptive paperbase selected
5 from the group consisting of coated, calendered paper; coated, uncalendered
paper and cast coated paper; the ink-receiving layer being present on the
coated paperbase from about 3 grams per square meter to about 7 grams per
square meter, and the coated paperbase having a Sheffield smoothness less
than approximately 20 and a Sheffield porosity less than approximately 10.
- 10
2. (Previously Presented) The print medium of claim 1, wherein the ink-
receiving layer is present from approximately 4 grams per square meter to
approximately 6 grams per square meter.
- 15
3. (Original) The print medium of claim 1, wherein the ink-receiving
layer comprises at least one water-soluble polymer, a cross-linking agent, a
mordant, inorganic particles, and at least one surfactant.
- 20
4. (Original) The print medium of claim 3, wherein the at least one wa-
ter-soluble polymer comprises at least one polyvinyl alcohol; the cross-linking
agent comprises boric acid; the mordant comprises a least one of diallyldi-
methyl-ammonium chloride, a cationic latex, or aluminum triformate; and the
inorganic particles comprise cationic, superfine colloidal silica.
- 25
5. (Canceled)

6. (Previously Presented) The print medium of claim 3, wherein the at least one surfactant comprises at least one nonionic, organosilicone surfactant.

5

7. (Previously Presented) The print medium of claim 3, wherein the at least one surfactant is at least one polysiloxane-polyethylene oxide compound or at least one polysiloxane-polyethylene oxide polypropylene oxide compound.

10

8. (Canceled)

9. (Withdrawn—currently amended) A method of forming a print medium having improved image quality and permanence, comprising:

15 providing a coated paperbase selected from the group consisting of coated, calendered paper; coated, uncalendered paper and cast coated paper; and

applying an ink-receiving layer to the coated paperbase at less than approximately 10 grams per square meter, the coated paperbase having a
20 Sheffield smoothness less than approximately 20 and a Sheffield porosity less than approximately 10.

10. (Canceled)

11. (Withdrawn) The method of claim 9, wherein applying an ink-receiving layer to the coated paperbase at less than approximately 10 grams per square meter comprises applying the ink-receiving layer from approximately 3 grams per square meter to approximately 7 grams per square meter.

5

12. (Withdrawn) The method of claim 9, wherein applying an ink-receiving layer to the coated paperbase at less than approximately 10 grams per square meter comprises applying a coating composition comprising at least one water-soluble polymer, a cross-linking agent, a mordant, inorganic particles, and at least one surfactant.

10

13. (Withdrawn) The method of claim 12, wherein applying an ink-receiving layer to the coated paperbase at less than approximately 10 grams per square meter comprises applying a coating composition comprising at least one polyvinyl alcohol; boric acid; at least one of diallyldimethylammonium chloride, a cationic latex, or aluminum triformate; cationic superfine colloidal silica; and at least one polysiloxane-polyethylene oxide compound.

15

14. (Withdrawn) The method of claim 12, wherein applying an ink-receiving layer to the coated paperbase at less than approximately 10 grams per square meter comprises applying the ink-receiving layer from approximately 4 grams per square meter to approximately 6 grams per square meter.

20

15. (Withdrawn) The method of claim 9, wherein applying an ink-receiving layer to the coated paperbase at less than approximately 10 grams

25

per square meter comprises coating the ink-receiving layer on the coated paperbase at less than approximately 10 grams per square meter.

16. (Withdrawn—currently amended) A method of printing an image
5 having improved image quality and permanence, comprising:
providing a print medium comprising
a coated paperbase selected from the group consisting of coated, cal-
endered paper; coated, uncalendered paper and cast coated paper;
and an ink-receiving layer present on the coated paperbase at less
10 than approximately 10 grams per square meter, the coated paperbase having
a Sheffield smoothness less than approximately 20 and a Sheffield porosity
less than approximately 10; and
printing the image on the print medium.

- 15 17. (Canceled)

18. (Withdrawn) The method of claim 16, wherein providing a print medium comprising a coated paperbase and an ink-receiving layer present on the coated paperbase at less than approximately 10 grams per square meter
20 comprises providing the ink-receiving layer on the coated paperbase from approximately 3 grams per square meter to approximately 7 grams per square meter.

19. (Withdrawn) The method of claim 16, wherein providing a print medium comprising a coated paperbase and an ink-receiving layer present on
25

the coated paperbase at less than approximately 10 grams per square meter comprises providing the ink-receiving layer comprising at least one water-soluble polymer, a cross-linking agent, a mordant, inorganic particles, and at least one surfactant.

5


20. (Withdrawn) The method of claim 16, wherein providing a print medium comprising a coated paperbase and an ink-receiving layer present on the coated paperbase at less than approximately 10 grams per square meter comprises providing the ink-receiving layer comprising at least one polyvinyl
10 alcohol; boric acid; at least one of diallyldimethylammonium chloride, a cationic latex, or aluminum triformate; cationic, superfine colloidal silica; and at least one polysiloxane-polyethylene oxide compound.

Respectfully submitted,

Chen

5

Hewlett-Packard Company
1000 NE Circle Blvd MS 422B
Corvallis, OR 97330


W. Bradley Haymond
Reg. No. 35,186
Attorney for Applicant
Telephone: (541) 715-0159

10

I hereby certify that this correspondence is
being deposited on **July 20, 2006**, with the
United States Postal Service as first class mail in an
envelope addressed to: Assistant Commissioner
for Patents, Washington DC 20231

15



Signature

W. Bradley Haymond

20

Typed Name

July 20, 2006

Date of Signature